

Patent Apples: (NAGA-) NAGAI DENSHI KOGYO

Abstract (Basic): JP 62094912

Mfr. of capacitor comprises forming (a) a valve-functioning metal film on one or both sides of an insulating material by vacuum evapn. plating; (b) forming an anodic oxide film on the film, (c) coating with a TCNQ complex by vacuum evapn. plating to form an organic semiconductor film; (d) coating a metal on the organic semiconductor film by sputtering to form a cathode film to obtain a basic element; and (e) coiling the basic element and providing electrode lead parts on both ends of the coiled element.

The insulating material is made of a plastic film or plastic sheet. The TCNQ complex includes 2,2'-bipyridinium (TCNQ)₂, 4-hydroxy-N-benzylanilinium (TCNQ)₂, 4-amino-2,3,5,6-tetramethyl anilinium (TCNQ)₂, pyridinium (TCNQ)₂, 4-cyano-N-methylpyridinium (TCNQ)₂, N-ethylquinolinium (TCNQ)₂, N-(2-phenetyl)quinolinium (TCNQ)₂.

USE/ADVANTAGE - The capacitor does not have any spacer but has the TCNQ complex-contg. organic semiconductor film, and the temp. stability is improved.

MANUFACTURE OF TOROIDAL ELECTROLYTIC CAPACITOR

Patent number: JP62094912
Publication date: 1987-05-01
Inventor: SAKAMOTO KIYOSHI; NARISAWA KUMIKO
Applicant: NAGAI DENSHI KOGYO KYODO KUMIA
Classification:
- international: H01G9/02; H01G9/05; H01G9/24
- european:
Application number: JP19850235933 19851021
Priority number(s): JP19850235933 19851021

Abstract not available for JP62094912

Data supplied from the **esp@cenet** database - Worldwide